



Preparation, Characterization of $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$ and Investigation of the Photocatalytic Degradability on Congo Red textile dye

Mohammed Zuheir Hassan*, Nada Y. Fairouz

Babylon university/ college of science/ Hilla/ Iraq

Abstract : A new photo catalyst ($\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$) was prepared by using of the co-precipitation method by mixing two different metal nitrate include of chromium(III) nitrate [$\text{Cr}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$] with silver nitrate AgNO_3 in different values and was calcinated in three different temperatures (400°C , 500°C & 700°C), and then its effectiveness for the photocatalytic activity for the degradation of Congo red as a textile dye was done to optimize the best photocatalyst and was found that (Cat-3C-) was the best for the photodegradation of Congo red, and with removal percentage (69.35%) when the concentration of Congo red was (40 ppm) with weight of catalyst (0.15 g) at room temperature. The characterization of the prepared catalysts had been carried out by the XRD & SEM and has been found that the appointed catalyst ($\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$) was successfully prepared. And then some studies had been performed to optimize the reaction effective parameters on the photocatalytic degradation of Congo red such as: catalyst weight, initial concentration of the dye solution. The best catalyst's weight was (0.07g) and the concentration of the dye was (10ppm).

Keywords: Heterogeneous photocatalytic, chromium (III) nitrate, silver nitrate, $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$, Congo red, XRD and SEM.

Introduction:

One of the biggest troubles that facing our countries in the last centuries is water pollution especially by the wastes of the industrial wastewater because it is high soluble in water and need for many hours and days unless need for many years to be degraded by the sunlight alone. So the advanced oxidation processes (AOPs) are used to remediate this problem and the heterogeneous photocatalytic process is one of the most important method used to damage these organic and inorganic wastes.¹⁻⁴

When someone thinking about the wastewater treatment, in the beginning he has to think about both the feasibility of the treatment and consideration of the economics sides of the process. There are different types of techniques available to the remediation of the organic contaminants in the wastewater such as chemical, physical, physicochemical and biological processes⁵.

Heterogeneous photocatalytic processes can be easy understood, and that is due to its definition as the employing under irradiation of steady solid semiconductor (such as TiO_2) for stimulating a reaction of the solid/solution interface⁷, It is impressive to know how the photocatalytic processes work, when the incident light (hv) energy by a UV-lamp on a semiconductor is been equal to or higher than the band gap energy of the semiconductor it will excite the electron from the valence band (VB) which is full of electrons at zero Kelvin to the conduction band (CB) which is empty at the zero Kelvin, left a hole in the valence band and that what is called excitons (e^-/h^+) then the generated electron and hole transfer to the surface of the semiconductor, where

the semiconductor acts in two types of reactions, acts as a donor for electrons when the promoted electron enter in reduction reaction with the species on the surface, while it acts as an acceptor for electron when the positive hole participates in an oxidation reaction Figure-1.^{8,9}

Mechanisms of releasing oxidizing species:

The heterogeneous process was a very complicated process because the oxidizing pathway wasn't very clear until Jean-Marie Herrmann suggested that the heterogeneous process can be divided into five steps¹⁰:

1. Transferring of reactants to the surface.
2. Adsorption of one of the reactants.
3. Reactions of the reactants in the adsorbed phase.
4. Desorption of the product(s).
5. Diffusion of the product(s) from the surface.




Figure-1- the simplified photocatalytic process on TiO₂ surface.

In the heterogeneous photocatalytic process not all the semiconductors have high photo-activity, because of the recombination process that occurred between the photohole and photoelectron, so one of the most important remediation methods is the doping of metal on the surface of the semiconductor, the activity can be increased by adding a noble metal or a metal from the transitional series of the periodic table. The metal doped on the surface of the semiconductor acts as a capture for the released electrons by the exerted UV light on the photocatalyst¹¹ the electron migrated to the conduction band and then trapped by the metal to avoid the recombination process, while the hole migrates to the surface of the photocatalyst and participates in an oxidation process with the adsorbed water or other organic compounds as the schematic figure(2). As an example for the metal doped a semiconductor Ag/TiO₂ and Pt/TiO₂ (prepared by the photoreduction deposition process and the chemical vapor deposition "CVD")¹².




Figure-2- Metal deposition on the surface of the semiconductor and the process of trapping the electron by the metal.

Figure 3, shows the chemical structure of Congo red dye, it absorbs the electromagnetic spectrum at $\lambda_{\max}=497\text{nm}^{13}$.




Figure-3- The structure of Congo red.

Lanping Zhang *et al.* (1997)¹⁴ prepared chromium oxide films on Pt(111) with thickness ranging from less than monolayer to more than eight monolayer, they found that chromium oxide grows with two different type structures on the Pt(111) surface depending on coverage and temperature. Zorica V. *et al.* (2002)¹⁵ activate by mechanically state for an equimolar of ZnO and Cr₂O₃ powder mixture by grinding using a high vibrational grinder for 0-180 min, and found that the activity of powders increases with increasing the grinding time and this is an indicator for the activity of spinels increase with decreasing of the grain size of the powdered spinel. Shahid Khan Durrani *et al.* (2012)¹⁶ synthesized some transition nanosized metal chromite spinels by using hydrothermal process and made a characterization by XRD, SEM and thermogravity technique. And found that nanocrystalline transition metal chromite spinels such as CoCr₂O₄ (bluish-green), MnCr₂O₄ (grayish-green), Cu_{0.5}Mn_{0.5}Cr₂O₄ (green), NiCr₂O₄ (sage green), CuCr₂O₄ (blackish-green), and Ni_{0.8}Cu_{0.2}Cr₂O₄ (dark green) were synthesized successfully through a hydrothermal method.

Materials and methods

Silver nitrate AgNO₃ and Chromium(III) nitrate nonahydrate [Cr(NO₃)₃.9H₂O] (Hopkin& Williams).

Ag₂O/Cr₂O₃ was prepared by Co-precipitation method¹⁷, different percentages of AgNO₃ silver nitrate and Chromium nitrate nonahydrate Cr(NO₃)₃.9H₂O dissolved in distilled water and were mixed together and transferred to a beaker (400ml) and filled to the mark with distilled water put on a hot plate magnetic stirrer. The temperature was fixed about (65°C-75°C) with continuous stirrer, NaOH (8N) drop-wise was added to the mixture and the pH maintained by a pH meter at (7.5-9.5), then obtained precipitate was left on the hot plate for 1 hour with continuous stirrer.

The obtained precipitate was washed with a hot distilled water for many times in order to eliminate the undesired sodium ions, until pH of obtained washing water close to the neutral medium (pH=7.0) it means that the precipitate is free of sodium ions, and the precipitate was dried in an oven at about (100°C) then the precipitate was triturated in a ceramic mortar to make homogenous particle Figure-4-.

The last step was calcination of the precipitate in different temperatures (a)400°C (b)500°C and (c)700°C for 4 hours. The obtained precipitates was (green-brown) color and was characterized by X-ray diffraction (XRD) and Scanning electron microscope (SEM).




Figure-4- Co-precipitation reactor.

Characterization process:

In this work, the prepared catalysts characterized by using XRD (Rigaku- MiniFlex II Desktop X-ray Diffractometer) and the crystallite size was determined from Scherrer's equation eq.-6-, where it was prepared as a homogenous powder, (1 g) of the catalyst was placed on a slide put in front of the path of the X-ray.

$$D = \frac{k\lambda}{\beta \cos\theta} \dots\dots(6)$$

Where D is mean crystalline size, k is the Scherrer's Constant or that which is called the shape factor because it depends on the shape of the crystal and its value is (0.94), λ is wavelength of the X-ray radiation (0.15406 nm for $\text{CuK}\alpha$), β is the full width of half-maximum (FWHM) intensity of the appeared peak explained in radians (Actually, β is measured in degrees but to unitizing the units of the equation β multiple by $(\pi/180)$ to transmute to the radians and lastly θ is the diffraction Bragg's angle¹⁸. Scanning electron microscope(SEM) [INSPECT S50] was used to determine the morphology of the prepared photocatalyst and the crystallography, a bit weight of the catalyst was taken and coated with a thin carbon layer and fixed on a plate and exposed to an electron beam.

Applications of the prepared photocatalysts: Many applications for the prepared photocatalysts were carried out to determine the optimum conditions for photocatalytic degradation of Congo red as a textile dye, by using high pressure mercury lamp (125 watts), with light intensity (7.1 mW/cm^2) at (5cm) distance between lamp and the photocell.

Examination of the photocatalytic activity: The examining of the photocatalytic activity of the prepared $\text{Ag}_2\text{O/Cr}_2\text{O}_3$ was made, a (0.15g) of the different prepared photocatalysts was taken with (100ml) of (40ppm) of Congo red, and put in the photoreactor at (298 K) and (7.1 mW/cm^2) light intensity at pH=7.

Determination of the adsorption time: To begin the study of the optimum conditions, at the beginning we have to determine the adsorption time of the photocatalysts to insure that most of dye molecules are adsorbed on the surface of the photocatalyst, so for the most active photocatalyst of prepared $\text{Ag}_2\text{O/Cr}_2\text{O}_3$ (0.07g) was taken with (100ml) of (10ppm) of Congo red at (298K) and (7.1 mW/cm^2).

Effect of catalyst's weight on the photocatalytic degradation of Congo red: This process occurred by making many experiments by using different weights of the photocatalyst (0.03, 0.05, 0.07, 0.1 and 0.25g) respectively, one experiment for each weight alone, then different weights of $\text{Ag}_2\text{O/Cr}_2\text{O}_3$ were added to (100ml) of Congo red, here is all the other conditions were kept constant such as concentration of Congo red was (10ppm), temperature was (298K), pH=7, light intensity was (7.1 mW/cm^2).

Effect of concentration of Congo red with constant weight of $\text{Ag}_2\text{O/Cr}_2\text{O}_3$: Different concentrations of Congo red were taken in different experiments (10, 15, 20 and 25ppm) with (0.07g) of $\text{Ag}_2\text{O/Cr}_2\text{O}_3$ in (100ml) of the dye at (298K), (7.1 mW/cm^2) was the light intensity and pH=7.

Results and Discussion:

X-ray diffraction of $\text{Ag}_2\text{O/Cr}_2\text{O}_3$ prepared at different ratios of $\text{Ag}_2\text{O:Cr}_2\text{O}_3$ and comparison to the metallic Ag_2O and Cr_2O_3 :

X-ray diffraction was taken for the prepared photocatalysts that were prepared at different ratios and were calcinated at (700°C) in figure-5-:




Figure-5:- XRD patterns of Ag_2O/Cr_2O_3 prepared in different percentages and calcinated in ($700^\circ C$) and compared to Cr_2O_3 .

Figure-5- is an obvious evidence for the good interface and constitution of Ag_2O/Cr_2O_3 comixed semiconductor and showed the existence of the Cr_2O_3 peaks and the peaks of silver oxide (Ag_2O) and was a shift in the peaks positions and intensities noticed relative to the formation of a new phase of the semiconductor and is (Ag_2O /Cr_2O_3) mixture of the silver oxide on the chromium oxide (Cr_2O_3) surface, for (Cat-1-) there were many peaks (38.1409° and 44.3242°) return to Ag_2O and (31.1919° , 36.0784° and 39.9502°) return to the Cr_2O_3 with consulting of the intensities percentages of the appeared peaks in the XRD charts,(Cat-2-) was nearly the same for (Cat-1-), because it appears three peaks two peaks at (38.1584° and 44.3366° , 64.4°) for Ag_2O alone and the third is for Cr_2O_3 standard peak at (36.0884° , 62.2119°), as the strongest peaks, but there is very few shift in the peak's position¹⁹.

For (Cat-3-) it was the second most intense peak was the peak of the new phase Ag_2O/Cr_2O_3 at (29.0479°) with an intensity approach to (94%) and there were other peaks observed for chromium oxide phase

at (36.1503 °, 39.6341°, 41.6710° & 62.2337°), that means that the phase of Ag₂O was less number of peaks in the chart of the XRD as (38.3651° & 44.1322°) with an intensity percentages (3% and 11%) respectively.

For the (Cat-4-) here is the peak of the new phase Ag₂O-Cr₂O₃ was appeared at (28.9664°) but with less intensity percentage was (51%) and the other strongest peaks was for Cr₂O₃ phase were at (33.6330°, 36.0860°, & 39.9362°, 41.5158°), and it was one peak of Ag₂O phase at (44.0356°) but with small intensity (7%), that was all to insure us that is with the decrease of the Ag₂O percentage decreases the number of peaks and its attribute.

Calculations of the mean crystallite size of (Ag₂O/Cr₂O₃):

From the X-ray diffraction the mean crystallite size of the Ag₂O doped Cr₂O₃ was calculated and the impact of Ag₂O loaded on the crystallite weight, Both figure 6, and table 2 showed that the increase in the ratio of silver oxide loaded on the Cr₂O₃, it will decrease the mean crystallite size until the ratio became (20:80)% of (Ag₂O:Cr₂O₃)% it will relatively increase, because of the crystallite size of the silver oxide is smaller than that of Chromium oxide. And the above results summarized in Figure-6-:

Scanning Electron Microscope (SEM):

This technique was used to study the structures of the prepared photocatalysts from the aspect of the morphology of crystals of the semiconductors using the SEM's tip of the electron gun, the prepared photocatalysts Ag₂O/Cr₂O₃ were compared with the standard materials (Ag₂O& Cr₂O₃):




Figure -6-: Effect of the Ag₂O loaded on the chromium oxide on the mean crystallite size of the prepared Ag₂O/Cr₂O₃ at different ratios and calcinated at (400°C) and compared to Cr₂O₃.




Figure-7-: SEM of (a)Ag₂O-Cr₂O₃ (40:60)% calcinated in 400°C (b) Cr₂O₃.

a comparison was made, so the prepared $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$ was more rigidity than the Cr_2O_3 alone because the last was a small grains as it shown in figure -7-(b), then the new phase was more rigidity material than Cr_2O_3 . And it was not a homogeneous grains like Cr_2O_3 , and the heterogeneous shape due to the uncontrolled mortaring²⁰.

Examination of the photocatalytic activity of the prepared photocatalysts

The photocatalytic activity for the prepared photocatalysts $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$ was determined by the removal percentages as in figure-10-:




Figure-10-: Photocatalytic activity of the prepared $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$.

The best photocatalytic activity catalyst was determined from the above figure and table and it was (69.35%) for the sample Cat-3C- that it ratio was (40:60)% of ($\text{Ag}_2\text{O}:\text{Cr}_2\text{O}_3$) and which was calcinated at (400°C), because it gives smaller band gap to transfer more electron for the increase of the photoreaction and decreasing of the electron/hole recombination, and also because the small mean crystallite size (**17.01 nm**) of Cat-3C- that was increased the surface area that will increase number of active site on the surface of the photocatalyst which upon it the adsorption process was proceeded.

Determination of the adsorption time:

This process is to determine the time that all the dye molecule placed in the active sites and all the active sites are all full, to increase the photocatalytic efficiency by increasing number of degraded molecules of Congo red figure -11-.




Figure-11-: The determining of the adsorption time of the photocatalyst $\text{Ag}_2\text{O}/\text{Cr}_2\text{O}_3$ (Cat-3C-).

It was investigated that the adsorption time of Ag_2O/Cr_2O_3 becomes constant when the time of the adsorption reaction reached (40 minutes) then the adsorption reaction was at an equilibrium state where there was no empty active sites to adsorb the molecules of the dye on the surface of the photocatalyst so the reading of the concentration became approximately fixed.

Effect of the catalyst's weight:

It was notified that the concentration of Congo red approach to zero for each weight of catalyst after (60minutes) of irradiation time and the linear equation relation with the irradiation time and from figure-12- it was notified that the rate of photoreaction increases with increasing the weight of the catalyst in the photoreaction's mixture until reached the tip of the plateau at (0.07 g) and then the rate of photoreaction began decreasing gradually with the increase in the weight of the photocatalyst, where the rate of photoreaction at the plateau region was (0.044 min^{-1}) as the most rate of photoreaction.

The increasing in the weight of catalyst increases the number active sites available for the adsorption process on the surface of the photocatalyst which increases the number of adsorbed molecules of the dye on the surface of the photocatalyst which increases the number of utilized photons of the incident light and also increase of releasing the number of $\cdot OH$ and $O_2^{\cdot -}$ radicals then the rate of degradation increased, this increment continues until reach the tip of the plateau or the optimum catalyst's mass²¹⁻²⁵, then the reaction rate began decreasing with the increase in the weight of the photocatalyst because of the accumulation of an excess number of the photocatalyst's particles(number of adsorbed dye not sufficient to fill the active sites of Ag_2O/Cr_2O_3) which might reduce the transmitted incident UV-light through the solution, so the number of degraded molecules will be decreased then the measured concentration of the dye will be high that which decreases the reaction rate, in general the photocatalytic efficiency depends on the equilibrium between the number of utilized photons and the number of active sites on the surface of the semiconductor, then the excess additional amount of the photocatalyst does not enhance the photocatalytic process²⁶⁻³⁶




Figure-12-: Effect of mass of catalyst on the photocatalytic degradation of Congo red, concentration of the dye is (10 ppm) with different weights of Cat-3C- of Ag_2O/Cr_2O_3 at pH=7 at temperature (298.15 K) with light intensity (7.1 mW/cm^2).

Effect of the initial concentration of Congo red:

The results listed in indicate that the decomposition rate of the dye depends on the initial concentration of the dye, so when increase of the irradiation time the remaining concentration (C_t/C_0) of Congo red will be decreased at using of Ag_2O/Cr_2O_3 (Cat-3C-) with a weight (0.07 g), but it increases with increasing the taken initial concentration of Congo red from an experiment to another, that means the increase in the initial concentration of the dye decreases the rate of reaction as in figure-13-, when the concentration of the Congo red was (10 ppm) the reaction rate was (0.044 min^{-1}), but when the concentration of Congo red was (25 ppm) the reaction rate was reduced to (0.004 min^{-1}) that is absolutely slower than that of concentration of (10 ppm), this behavior due to that when the molecules of the dye adsorbed on the surface of the photocatalyst the active sites of the photocatalyst it all will be occupied by the adsorbed molecules of dye, but after the addition of an excess number of dye molecules it will be accumulated on the first adsorbed layer of molecules made another layer which is not adsorbed molecules that which affect the utilization of the incident light on the surface and the transmitted light will be reduced because it was well blocked by the accumulated layers of the excess concentration of the Congo red³⁷⁻⁴³




Figure-13-: Effect of concentration of Congo red on the photocatalytic efficiency, weights of Cat-3C- of $Ag_2O-Cr_2O_3$ was (0.07g) at pH=7 at temperature (298.15 K) with light intensity (7.1 mW/cm^2).

Conclusion:

Ag_2O/Cr_2O_3 was successfully prepared and characterized by XRD and SEM and with average mean crystallite size 17.01nm, the best Ag_2O/Cr_2O_3 prepared catalyst in the photoactivity was (Cat-3C-) with percentage (40:60) calcinated at 400°C . From the results we can conclude that the optimum mass of catalyst for Ag_2O/Cr_2O_3 was 0.07g for degradation of Congo red that its concentration was 10ppm at 25°C and $7.1 \text{ (mW/cm}^2\text{)}$ light intensity.

Acknowledgment:

I wish to thank Babylon University, the Faculty of science, and the Department of Chemistry for offering me the scholarship and related facilities.

References:

1. Lee, M. (2008). Degradation of Dyes Using Zinc Oxide as the Photocatalyst, Thesis, UNIVERSITI PUTRA MALAYSIA.
2. Miguel, R. (2003). Fenton and UV-vis based advanced oxidation processes in wastewater treatment: Degradation, mineralization and biodegradability enhancement, UNIVERSITAT DE BARCELONA.
3. Alkaim, A. F.; Sadik, Z.; Mahdi, D. K.; Alshrefi, S. M.; Al-Sammarrarie, A. M.; Alamgir, F. M.; Singh, P. M.; Aljeboree, A. M., 2015. Preparation, structure and adsorption properties of synthesized multiwall carbon nanotubes for highly effective removal of maxilon blue dye, *Korean J. Chem. Eng.*, 32: 2456-2462.
4. Alkaim, A. F.; Dillert, R.; Bahnemann, D. W., 2015., *Environ. Technol.*, 36: 2190–2197.
5. Heponiemi, A. and Lassi, U.(2012) "Advanced Oxidation Processes in Food Industry Wastewater Treatment – A Review", ISBN 978-953-307-905-9, *InTech*.
6. Ameta P., Kumar A., Paliwal M., Ameta R. and Malkani R. K., (2007), Photocatalytic Bleaching of Rose Bengal by Some Coloured Semiconducting Oxides, *Bulletin of the Catalysis Society of India*, **Vol.** 6, pp.130-135.
7. Galvez, J. B. and Rodriguez, S. M.,(2003). "Solar Detoxification", *Plataforma Solar de Almeria*, Spain.
8. Falah H. H., (2011), Photochemical Treatments of Textile Industries Wastewater, *Chemistry Department, College of Science, Babylon University, Iraq, InTech*.
9. Nicholas T. N., (2010). Sol-Gel Synthesis and Characterization of Novel Metal Oxide Nanomaterials for Photocatalytic Applications, Doctoral thesis, *Dublin Institute of Technology*.
10. Herrmann, J.-M., (1999). Heterogeneous photocatalysis: fundamentals and applications to the removal of various types of aqueous pollutants, *Catalysis Today*, 0920-5861, Vol. 53, pp. 115-129.
11. Julian B. G., and Sixto M. R. (2003), Solar Detoxification, *Plataforma Solar de Almeria, Spain*, United Nations Educational, Scientific and Cultural Organization.
12. Chia-H. Li, Yung-H. H., Wan-T. C., Chin-C. L. and Chao-L. K., (2007), Study on preparation and photocatalytic performance of Ag/TiO₂ and Pt/TiO₂ photocatalysts, *Separation and Purification Technology*, Vol.58, pp.148–151.
13. Pooja M. and Jyotsna K., (2013), Degradation of Congo Red Dye in Aqueous Solution by Using Phytoremediation Potential of *Chara Vulgaris*, *Chitkara, Chemistry Review* Vol. 1, pp. 67–75.
14. Zhang L., Kuhn M. and Diebold U., (1997), Growth, structure and thermal properties of chromium oxide films on Pt(111), *Journal of surface science*, 375, pp.1-12.
15. Zorica. V. M., Sreckovic T. V., Prelevic I. P. and Ristic M. M. (2002), Structural Changes of ZnO-Cr₂O₃ System during Mechanical Activation and Their Influence on the Spinel Synthesis, Belgrade, Yugoslavia, **Vol.** 10, pp.155-160.
16. Shahid. Kh. D., Hussain S. Z., SaeedKh., Khan Y., Arif M. and Ahmed N., (2012), Hydrothermal synthesis and characterization of nanosized transition metal chromite spinels, *Turk. J. Chem. (TUB ITAK)*, **Vol.** 36, pp. 111–120.
17. Prasad R. and Rattan G., (2010) Preparation Methods and Applications of CuO-CeO₂ Catalysts: A Short Review, *Bulletin of Chemical Reaction Engineering & Catalysis*, **Vol.** 5 (1), pp. 7 – 30.
18. Riahi-Noori N., Sarraf-Mamoory R. and Mehdikhani A., (2011), Synthesis of Combined ZnO/Additives Nano Powders by Gel Combustion Method for ZnO Varistors Usage, *International Conference on Chemical, Environmental and Biological Sciences (ICCEBS)*.
19. Lin X., Wu K., Shao L., Shui M., Jiang X., Wang D., Long N., Ren Y., Shu J., "Facile preparation of Cr₂O₃@Ag₂O composite as high performance lithium storage material", *Journal of Alloys and Compounds*, **Vol.** 598, pp. 68–72 (2014).
20. Suñol J.J., and Escoda L., (2007) "SEM and TEM studies in alloys developed by mechanical alloying", *Modern Research and Educational Topics in Microscopy*.
21. Fairouz, N. Y., 2016. Evaluation of new couple Nb₂O₅/Sb₂O₃ oxide for photocatalytic degradation of orange G dye, *International Journal of ChemTech Research*, 9: 456-461.
22. Aljeboree, A. M., 2016.. *International Journal of ChemTech Research*, Adsorption of crystal violet dye by Fugas Sawdust from aqueous solution 9(3): p. 412-423.
23. Al-Gubury, H.Y. 2016. The effect of coupled titanium dioxide and cobalt oxide on photo catalytic degradation of malachite green, *International Journal of ChemTech Research*, 9(2): p. 227-235.

24. Aljeboree, A. M.; Radi, N.; Ahmed, Z.; Alkaim, A. F., 2014. The use of sawdust as by product adsorbent of organic pollutant from wastewater: adsorption of maxilon blue dye, International Journal of chemical sciences, 12: 1239-1252.
25. Al-Gubury H. Y., Fairouz N. Y., Aljeboree A. M., Alqaraguly M. B., and Alkaim A. F., 2015. Photocatalytic degradation n-undecane using coupled ZnO-Co₂O₃, Int. J. Chem. Sci., 13(2): p. 863-874.
26. Al-Gubury, H. Y., Almaamory, E. S., Alsaady, H. H., and Almurshidy, G. S., 2015. Photocatalytic degradation of aquatic rhodamine B solution using ultraviolet light and zinc oxide, Research Journal of Pharmaceutical, Biological and Chemical Sciences, 6: 929-939.
27. Alqaragully M.B., AL-Gubury H. Y, Aljeboree A.M., Karam F.F., and Alkaim A. F., 2015, Monoethanolamine :Production Plant, Research Journal of Pharmaceutical, Biological and Chemical Sciences, 6(5): p. 1287-1296.
28. Kareem, A.; Abd Alrazak, N.; Aljebori, K. H.; Aljebori, A. M.; Alboory, H. L.; Alkaim, A. F., 2016., Int. J. Chem. Sci., 14: 635-648.
29. Abid, F. M.; Salman, J. M., 2012. Liquid chromatographic method for determination of biogenic amines in imported fish and meat products, Asian journal of chemistry, 24: 5763-5765.
30. Algubili A. M., Alrobayi E. M., and Alkaim A. F., 2015. Photocatalytic degradation of remazol brilliant blue dye by ZnO/UV process, Int. J. Chem. Sci., 13(2): p. 911-921.
31. Omran, A. R.; Baiee, M. A.; Juda, S. A.; Salman, J. M.; Alkaim, A. F., 2016. Removal of congo red dye from aqueous solution using a new adsorbent surface developed from aquatic plant (*Phragmites australis*), International journal of ChemTech Research, 9: 334-342.
32. Salman, J. M.; Al-Mamoori, A. M. J.; Al-Saadi, A. H.; al Terehi, M. N., 2012. Dna damage in common carp fish (*Cyprinus carpio* L.) induced by acute exposure to copper & cadmium, World Applied Sciences Journal, 20: 679-682.
33. Alkaim, A. F.; Hussein, F. H., 2012. Photocatalytic degradation of EDTA by using TiO₂ suspension, International Journal of Chemical Sciences, 10: 586-598.
34. Borhade A. V., Tope D. R., and Uphade B. K., (2012), An Efficient Photocatalytic Degradation of Methyl Blue Dye by Using Synthesized PbO Nanoparticles, E-Journal of Chemistry, Vol. 9, No. 2, pp. 705-715.
35. Al-Gubury H. Y., and Al-Murshidy G. S., 2015. Photocatalytic decolorization of brilliant cresyl blue using zinc oxide, International Journal of PharmTech Research, 8: 289-297.
36. Alkaim A. F., and Alqaragully M. B., 2013., Int. J. Chem. Sc., 11: 797-814.
37. Jabbar, A. Z.; Hadi, A. G.; Sami, F., 2014. Removal of azo dye from aqueous solutions using chitosan, Oriental Journal of Chemistry, 30: 571-575.
38. Hadi, A. G.; Humedy, E. H.; Saddam, N. S.; Abd-Alameer, F. S., 2016. Spectrophotometric study of complex formation between hematoxylin and Al³⁺ and Fe³⁺ ions, International Journal of PharmTech Research, 9: 292-298.
39. Abdulrazzak, F. H., 2016. Enhance photocatalytic activity of TiO₂ by carbon nanotubes, International Journal of ChemTech Research, 9: 431-443.
40. Hadi, A. G., 2016. Removal of Fe (II) and Zn (II) ions from aqueous solutions by synthesized chitosan, International Journal of ChemTech Research, 9: 343-349.
41. Karam, F. F.; Hussein, F. H.; Baqir, S. J.; Alkaim, A. F., 2016. Optimal conditions for treatment of contaminated waters with anthracene by Fenton processes in close system reactor, Journal of Chemical and Pharmaceutical Science, 9: 1111-1115.
42. Kamil, A. M.; Mohammed, H. T.; Alkaim, A. F.; Hussein, F. H., 2016. Adsorption of Congo red on multiwall carbon nanotubes: Effect of operational parameters, Journal of Chemical and Pharmaceutical Sciences, 9: 1128-1133.
43. Raheem, R. A.; Al-gubury, H. Y.; Aljeboree, A. M.; Alkaim, A. F., 2016. Photocatalytic degradation of reactive green dye by using Zinc oxide, journal of Chemical and Pharmaceutical Science, 9: 1134-1138.
