



Synthesis and characterization of copper nanoparticles using *Tridax procumbens* and its application in degradation of bismarck brown

V.N. Kalpana, Poulami Chakraborty, V. Palanichamy, V. Devi Rajeswari*

Department of Biomedical sciences, School of Biosciences and Technology, VIT University, Vellore –632 014, TamilNadu, India

Abstract : In the present work, copper nanoparticles (Cu NPs) have been synthesized by simple and green technique by using *Tridax procumbens* leaf extract. The formation of Cu NPs is monitored by recording the UV-Vis absorption spectra which showed surface Plasmon resonance at 320 nm. The green synthesized Cu NPs were further characterized by FT-IR, SEM and XRD. FT-IR identified the presence of active and phenolic groups. The crystalline morphology and size of the nanoparticles were determined by SEM and X-ray diffraction studies. The average particle size of Cu nanoparticles was found to be in the range of 71 nm. These biologically synthesized Cu NPs were tested for antimicrobial activity against five pathogens. The Cu NPs were also used for the remediation of a Bismarck brown dye. Approximately, 89% degradation of Bismarck brown dye was observed within 72 hours using Cu NPs. The mechanism involved in the degradation of dye and its phytotoxicity study has been presented. The overall outcome of this study suggests that the green synthesis of Cu NPs hold promise as a potent antimicrobial and antioxidant agent. The particles obtained were also found to degrade Bismarck brown dye.

Keywords: Cu NPs, Bismarck Brown, Phytotoxicity, Antioxidant activity, UV-Vis.

Introduction

Over the past few years, nanotechnology plays a very important role in modern research^[1]. This technology deals with the synthesis of nanoparticles with controlled size, shape and dispersity of materials at the nanometer scale length^[2]. Plant mediated synthesis of nanoparticles has achieved a keen interest due to its eco-friendly and low time consuming properties^[3]. Biological methods of synthesizing nanoparticles using Plants, microorganisms and enzymes have several advantages over conventional physical and chemical methods^[4]. Copper nanoparticles (Cu NPs) have recently attracted a particular attention because of their lower-cost, extensive availability and various applications in the field of sensors, catalysis, inkjet etc.^[5-8]. However, these Cu NPs have relatively lower redox potential, and it is prone to oxidation when it is exposed to air. Hence, the synthesis of Cu NPs is a very challenging task. Cu NPs are generally synthesized by hydrothermal method, microwave assisted pyrolysis method, thermal reduction etc. However these methods are costly and utilize harsh organic solvents^[6]. Therefore, environmentally good synthetic methodologies are preferable. Based on this pursuit, the leaves of *Tridax procumbens* were utilized for the synthesis of Cu NPs.

Dyes are a major class of synthetic organic compounds which are released by industries such as paper, leather, food, textile etc. Dyes may be of different types such as azo, basic, acidic, anthraquinone etc^[9]. These organic pollutants may induce skin irritation, blood disorder, liver and kidney damage. Thus, the consequence necessitates the development of methods for the degradation of synthetic dyes^[10]. Degradation of these

compounds to non-toxic products is very difficult because of their high stability^[11]. Recently, nanoparticles of noble metals have gained importance in reduction and degradation of dye due to their stability and high catalytic activity

Thus, the aim of the present study is to develop a safe, cost-effective, non-hazardous method for the synthesis of Cu NPs using an aqueous extract of *Tridax procumbens* and its application in dye degradation.

Experimental details

Materials

All the reagents used in this experiment were obtained from Sigma Aldrich chemicals. Double distilled water was used throughout the experiments. Filtration was established by using Whatman No.1 filter papers. Glasswares used for the complete reactions were washed well, rinsed with double distilled water and dried in hot air oven.

Preparation of aqueous extract of *Tridax procumbens*

The fresh *Tridax procumbens* leaves were collected from VIT University, Tamil Nadu, India. The leaves were thoroughly washed several times using distilled water to remove impurities. The cleaned leaves were dried subsequently under sunshade to remove the moisture completely and then it is powdered by using mechanical grinder. The 5g of powdered plant leaves were taken into a beaker along with 100 ml of distilled water and allowed to boil at 60°C for 30 minutes. The prepared solution was filtered through Whatmann No.1 Filter paper. The extract was stored in a refrigerator at 4 °C for further use^[10, 12-13]

Phytochemical analysis

The fresh leaf extract of *Tridax procumbens* was used for Phytochemical screening. It was been carried out by standard phytochemical methods^[12, 14-15]

Biosynthesis of copper nanoparticles

For the synthesis of copper nanoparticles (Cu NPs) 25 ml of fresh leaf extract of *Tridax procumbens* was added to 75 ml of 1mM aqueous copper acetate. It was stirred for about 3 hours. Then, the solution was dried at 60°C in the oven^[13-14, 2]

Characterization of Copper nanoparticles

The formation of copper nanoparticles was confirmed by UV-Visible spectroscopy. Size of the Cu NPs was analyzed by UV in the range between 300-700 nm. FTIR analysis was carried out to find out the bio-molecules which is responsible for the reduction of copper ions. The structure of copper nanoparticles were determined by X-Ray diffraction analysis. Morphology and mean particle size were determined by SEM analysis^[10, 17]

Application Studies

Antioxidant activity (Hydrogen peroxide scavenging assay):

The hydrogen peroxide scavenging assay was assessed by the method using aqueous leaf extract of *Tridax procumbens*. Hydrogen peroxide (40mM) solution was prepared in phosphate buffer (pH 7.4). Extracts and Cu NPs (100 µg/ml) were added to a 40mM hydrogen peroxide solution. The reaction mixture was incubated for 10 min at RT. After incubation, the reaction mixture read at 230 nm against the blank solution with phosphate buffer solution^[18-19]. The inhibition percentage was calculated based on the formula

$$\% \text{ of inhibition} = (A1 - A2) / A1 \times 100$$

Where A1-absorbance of Hydrogen peroxide ; A2- absorbance of the reaction mixture with extract.

Antibacterial activity:

The antimicrobial study of Cu NPs was evaluated against bacterial pathogens such as *E. coli*, *S. aureus*, *P. aeruginosa*, *Listeria* sp, *Proteus* sp by disc diffusion method. The plant extract and the synthesized Cu NPs were added to the sterilized disc and carefully dispensed on Muller-Hinton agar plates and incubated for 24 hours at 37°C. The Zone of inhibition was measured from the centre of the disc to the clear zone in millimeter and the results were recorded [20-21].

Catalytic reduction of Bismarck brown using Cu NPs and Plant extract:

Tridax procumbens mediated synthesized Cu NPs were tested against Bismarck Brown in the presence of UV light exactly at 365 nm. About 1 ml of Bismarck Brown (1x 10⁻⁴ M) was mixed with 25, 50, 75, 100 µl of Cu NPs [22-24]. Every 24 hour interval sample was collected and subjected to UV- Visible Spectroscopy

% of dye degradation was estimated by

$$\% \text{ Decolourization} = \frac{100 \times (C_0 - C)}{C_0}$$

Where C₀ is the initial dye concentration and C is the concentration of dye after catalytic degradation

Phytotoxicity study:

The study was carried out with degraded dye (Bismarck Brown) using the seeds of *Cicer arietinum*. The seeds were sterilized to discourage fungal growth by wiping them on the surface with 1.2% sodium hypochlorite solution [24-25]. Five seeds were placed in each petri plate and watered separately with 5ml samples of each degraded dye per day. Positive Control was set up with normal water and the untreated dye was used as negative control. The plates were regularly monitored regularly for germination. Seeds with emerging radical are considered to be germinated. The length of the radical (root) and plumule (shoot) and the germination rate (%) were recorded after 7 days.

Results and discussions:**Qualitative Phytochemical screening:**

The results of phytochemical screening were represented in Table (1)

Table (1): Results of Phytochemical analysis

S. No	Phytochemical Test	Reagents used	Interference	Result
1.	Alkaloid	Mayer' Reagent	Appearance of yellow cream ppt.	Positive
		Hager's Reagent	Formation of yellowish white ppt	Positive
2.	Carbohydrate Test	Molish's Reagent	Formation of Violet ring	Positive
		Benedict's Reagent	Formation of orange red ppt	Positive
		Fehling's solution	Formation of red ppt.	Positive
3.	Saponin test	Foam Test	Produce foam that lasts for more than 10 minutes	Negative
4.	Glycoside test	Modified Brontrager's Reagent	No formation of pink colour	Negative

5.	Phytosterol test	Salkowski's Test	Golden brown colour obtained	Positive
6.	Fats and Fixed oil test	Filter Paper press Test	No oily stain was obtained	Negative
7.	Resin test	Acetone Water Test	No Appearance of Turbidity	Negative
8.	Phenol test	Ferric Chloride Test	Appearance of bluish black ppt	Positive
9.	Tannin test	Gelatin Test	No formation of white ppt.	Negative
10.	Diterpenes test	Copper Acetate Test	No formation of bright green colour	Negative
11.	Flavonoids test	Alkaline Reagent Test	No intense yellow colour obtained	Positive
		Lead Acetate Test	Yellow ppt. obtained	Positive
12.	Proteins and amino acids test	Xanthoproteic Test	Formation of yellow colour	Positive

Characterization of Copper nanoparticles:

UV-Visible Spectroscopy:

UV-Vis Spectrophotometer monitored the reduction of Cu⁺ ions for the metal ions stability. The characterization of copper nanoparticles by UV-Spectrophotometer from the range 200-800 nm. The broad peak was obtained at 320 nm which is represented in fig.1.




Fig.1. UV-Visible Spectroscopy

FT-IR Analysis:

The FT-IR analysis is used to identify the capping and stabilizing capacity of the leaf extract. The FTIR bands of biosynthesized Cu NPs using leaf extract of *Tridax procumbens* were indicated at 3441.65 (Bond: N-H stretch), 3002.02 (Bond: C-H stretch). The present study revealed that the FTIR band proved the appearance of carboxylic acid, and strong aromatic ring, which may be responsible for the synthesis of copper Nanoparticles using *Tridax procumbens* (Fig.2).




Fig.2 FTIR Analysis

XRD Analysis:

XRD pattern with a sharp peaks at $2\theta = 40.52, 53.31$ and 71.69 corresponding to (111), (200) and (220) representing face centered cubic structure of copper and are obtained (JCPDS No. 851554). The average crystallite size estimated using the Debye-Scherrer formula was found to be about 87 nm. This is related to the polycrystalline nature of the nanoparticles. XRD pattern revealed the structure of the synthesized Cu NPs (Fig. 3).




Fig.3. XRD

SEM Analysis:

The typical SEM image shows that the product mainly consists of particle-like spherical and monodispersed distribution of particle sizes and the size ranges from 85 to 118 nm. However, further observation with high magnification reveals that these Cu nanoclusters are assembled by smaller nanoparticles, which exhibit good uniformity and the average diameter is about 54 nm (Fig.4).




Fig.4 SEM Analysis

Antioxidant activity:

Hydrogen peroxide scavenging assay:

100 μg of aqueous extracts of *Tridax procumbens* exhibited 29% scavenging activity on hydrogen peroxide and Cu NPs exhibits 38%. On the other hand, α- tocopherol exhibited 46.77% hydrogen peroxide scavenging activity (**Table 1**).

Table 1: Antioxidant activity

Samples	% H ₂ O ₂ Scavenging Activity (100 μg/mL)
Control	0
α-tocopherol	46.77
<i>Tridax procumbens</i> (leaves extract)	29
Copper Nanoparticles	38

Antibacterial activity:

The synthesized Cu NPs and aqueous plant extract *Tridax procumbens* had tested for its ability to inhibit the growth of *E. coli*, *S. aureus*, *P. aeruginosa*, *Listeria* sp, *Proteus* sp. The nanoparticles showed maximum inhibition against *E.coli* followed by *S.aureus*, *P. aeruginosa*, *Listeria* sp, *Proteus* sp. The plant extract showed maximum inhibition against *Pseudomonas aeruginosa* followed by *Listeria* sp, *S.aureus*, *Proteus* sp, *E. coli*. The zones are presented in Table. This result suggests that the copper nanoparticles and the plant extract have the potential against several bacteria species (Table 2)

Table 2. Antibacterial activity

Microorganism	Cu NPs (mm)	Plant Extract (mm)
<i>E. coli</i>	24± 0.36	6±0.47
<i>S. aureus</i>	18±0.87	10±0.91
<i>P. aeruginosa</i>	13±0.1	17±0.14
<i>Listeria</i>	9±0.41	13±0.23
<i>Proteus</i> sp	6±0.25	8±0.60

Catalytic reduction of Bismarck brown using Plant extract and Cu NPs:

Dyes with different concentration of Plant extract were observed from Fig. 5 (a) and (b) for decolourization. Bismarck Brown showed maximum degradation only at 72 hours (100μl Plant extract showed

71% decolourization, 75 μ l Plant extract showed 52% decolourization, 50 μ l plant extract showed 43% decolourization and 25 μ l plant extract showed only 32% decolourization).

Dyes with different concentration of Copper NPs were observed from Fig.6 (a) and (b) for decolourization. Bismarck Brown showed maximum degradation only at 72 hours (100 μ l Copper Nps showed 89% decolourization, 65 μ l Copper Nps showed 72% decolourization, 50 μ l Copper Nps showed 52% decolourization and 25 μ l Copper Nps showed only 38% decolourization).




Fig 5 Catalytic reduction of Bismarck brown using Plant extract





Fig 6 Catalytic reduction of Bismarck brown using Cu NPs

Phytotoxicity study:

This study was carried out to evaluate the relative sensitivities of *Cicer arietinum* towards the dye and their degradation products using seed germination and plant growth assays. Germination (%) of plant seeds was less with the raw dye when compared to the treatment of dye with Copper NPs. There was 100% Germination in control (Water). The germination (%) of *Cicer arietinum* was also found to be 100% when treated with degraded dye and the untreated dye showed only 40% germination (Fig.7) and **Table 3**.^[26] conducted similar studies using *Aloe barabardensis* extract to degrade two different dyes (malachite green and congo red), where the authors found the marked difference in the toxic effect of dyes on seedling compared with plant extract treated dye products.

Table 3: The germination (%) of *Cicer arietinum*

Treatments	<i>Cicer arietinum</i>	
	Plumule (cm)	Radicle (cm)
Control (Water)	24±0.67	8±0.70
Untreated Dye (Bismarck Brown)	8.5±0.55	4±0.04
Treated Dye (Bismarck Brown+ Cu NPs)	16±0.69	7.2±0.17



(a) Control (b) Untreated dye (c) Treated dye(25µl of Cu NPs) (d) Treated dye(50µl of Cu NPs) (e) Treated dye(75µl of Cu NPs) (f) Treated dye(100 µl of Cu NPs)

Fig.7 Phytotoxicity study - *Cicer arietinum***Conclusion:**

In the present work, we report an eco-friendly and simple method for the synthesis of Copper nanoparticles (Cu NPs) using *Tridax procumbens* leaf extract. Cu NPs has been synthesized using copper acetate as a precursor. The biosynthesized nanoparticles have been characterized by UV-VIS spectroscopy, FTIR, XRD and SEM. The biosynthesized Cu NPs showed excellent antimicrobial activity. Cu NPs also showed efficient catalytic activity towards degradation of Bismarck brown thus having potential for industrial application.

References

1. Mekala J; Rajan M R; Ramesh R. (2016). Green Synthesis and Characterization of Copper Nanoparticles Using Tulsi (*Ocimum Sanctum*) Leaf Extract. Paripex-Indian Journal of Research. DOI: 10.15373/22501991/February2016/4.
2. Hariprasad S; Susheela Bai G; Santhoshkumar J; Madhu C.H; Sravani D. (2016). Green synthesis of Copper Nanoparticles by Arevalanata Leaves Extract and their Anti Microbial Activities. International Journal of ChemTech Research. Vol. 9, No.02, pp98-105
3. Vanaja M; Paulkumar K; Baburaja M; Rajeshkumar, S; Gnanajobitha, G; Malarkodi, C; Sivakavinesan, M; and Annadurai G.(2014). Degradation of Methylene Blue Using Biologically Synthesized Silver Nanoparticles. Bioinorganic Chemistry and Applications. DOI: 10.1155/2014/742346
4. Shobha G; Vinutha, M; Ananda S. (2014). Biological Synthesis of Copper Nanoparticles and its impact - a Review. International Journal of Pharmaceutical Science Invention, Vol. 3, No. 8, pp. 28-38.

5. Shende, S; Ingle A.P; Gade A; Rai M; (2015). Green synthesis of Copper nanoparticles by *Citrus medica* Linn. (Idilimbu) juice and its antimicrobial activity. World J Microbiol Biotechnol 31, pp. 865–873.
6. Sinha T; Ahmaruzzaman M.(2015). Green synthesis of Copper nanoparticles for the efficient removal (degradation) of dye from aqueous phase. Environ Sci Pollut Res, Vol. 22 pp. 20092–20100.
7. Nuzhat Tabassum and Vidyasagar G. M.(2016). Synthesis, Characterization and Antimicrobial activity of Silver nanoparticles using Santalum album aqueous seeds extract International Journal of ChemTech Research.Vol. 9, No. 05, pp. 352-358
8. Vidhu, VK; Philip D. (2014). Catalytic degradation of organic dyes using biosynthesized silver nanoparticles. Micron 56, 54-62.
9. Badmapriya, D; Asharani I.V; (2016). Dye degradation studies catalysed by green synthesized Iron oxide nanoparticles ; International Journal of ChemTech Research 9(06), 409-416, 2016
10. Saranyaa devi, K; Subha V; Ernest Ravindran R.S; Renganathan S. (2014). Synthesis and Characterization of Copper Nanoparticle using *Capparis Zeylanica* leaf Extract; International Journal of ChemTech Research; Vol. 6, No.10, 4533-4541.
11. Sultana S; Ramabadran S; Swathi P.R. (2015). Photocatalytic Degradation of Azo Dye using Ferric Oxide Nanoparticle. International Journal of ChemTech Research 8(3), 1243-1247.
12. Harbone, J.B (1973). Phytochemical methods. A guide to modern techniques of plant analysis. Chapman and Hall, New York. 279
13. Mercy Ranjitham A; Selva Ranjani G; Caroling G. (2015). Biosynthesis, Characterization, Antimicrobial Activity Of Copper Nanoparticles Using Fresh Aqueous *Ananas Comosus* L. (Pineapple) Extract International Journal of PharmTech Research, Vol. 8 No. 4, 750-769.
14. Devi H.S; Singh T.D; (2014). Synthesis of Copper Oxide Nanoparticles by a Novel Method and its Application in the Degradation of Methyl Orange, Advance in Electronic and Electric Engineering. 4, 83-88
15. Venkatesan G; Chakravarthula S. N (2016). A Review on Ethnobotany, Phytochemistry and Pharmacology of *Boswellia ovalifoliolata* International Journal of ChemTech Research.Vol. 9 No. 01, pp. 95-104
16. Subhankari I; Nayak P.L (2013) .Antimicrobial Activity of Copper Nanoparticles Synthesised by Ginger (*Zingiber officinale*) Extract. World Journal of Nano Science & Technology, Vol. 2 No.1, pp. 2013 10-13.
17. Jayalakshmi, A; Yogamoorthi; (2014). Green synthesis of copper oxide nanoparticles using aqueous extract of flowers of *Cassia alata* and particles characterization, International Journal of Nanomaterials and Biostructures, Vol. 4, pp. 66-71
18. Subbaiya R; Selvam M.M; (2015). Green Synthesis of Copper Nanoparticles from *Hibiscus Rosasinensis* and their antimicrobial, antioxidant activities. Research Journal of Pharmaceutical, Biological and Chemical Sciences. Vol. 6 No. 2, pp. 1183-1190
19. Ganesan A; Thangapandian M; Ponnusamy, P; Sundararaj J.P; Nayaka S (2015). Antioxidant and antibacterial activity of parmelioid lichens from Shevaroy hills of Eastern Ghats, India International Journal of PharmTech Research. Vol.8, No. 9, pp. 13-23, 2015
20. Krishnamoorthy P; Jayalakshmi T;(2012). Preparation, characterization and synthesis of silver nanoparticles by using *phyllanthus niruri* for the antimicrobial activity and cytotoxic effects. J.chem.Pharma.Res. Vol. 4. No. 11, pp. 4783-4794
21. Panigrahi S; Mahapatra S; (2016). Evaluation of Antibacterial Activity of *Pongamia pinnata* L., *Curcuma longa* L. and *Mentha arvensis* L. Against *Staphylococcus aureus*. International Journal of ChemTech Research, Vol. 9 No.02, pp. 205-212.
22. Ganapuram BR; Alle M; Dadigala R; Dasari, A; Maragoni, V; Guttena V. (2015). Catalytic reduction of methylene blue and Congo red dyes using green synthesized gold nanoparticles capped by *Salmalia malabarica* gum. Int Nano Lett 5, pp. 215–222.
23. Sultana S; Ramabadran S; Swathi P.R; (2015). Photocatalytic Degradation of Azo Dye using Ferric Oxide Nanoparticle International Journal of ChemTech Research. Vol. 8, No. 3, pp. 1243-1247
24. Sinha, T; Ahmaruzzaman M; (2015). Biogenic synthesis of Cu nanoparticles and its degradation behavior for methyl red, Materials Letters. 159, pp. 168–171
25. Alhemediy A; Nader, S; Ebrahim, B.(2016). Impact of Silverleaf Nightshade(*Solanum elaeagnifolium* Cav.) organs powder on Germination and Growth of Wheat durum(Cham-5). International Journal of ChemTech Research. Vol. 9, No. 07, pp. 619-633.

26. Maithri,S; Rai,P; Rama Bhat,P; Prajna,P.S; Jayadev K; Venkatakrishna Rao P.S (2014). Degradation of malachite green and congo red using *Aloe barabadsensis* Mill. Extract. Int.J.Curr.Microbiol.App.Sci, Vol. 3(4), pp. 330-340
