



International Journal of PharmTech Research

CODEN (USA): IJPRIF, ISSN: 0974-4304, ISSN(Online): 2455-9563
Vol.15, No.02, pp 58-65, 2022

Natural Gums used in the preparation of Floating Drug Delivery System

Uma Rani*, M. Sumakanth, Asma Begum

Rbvrr Women's College of Pharmacy, Barkatpura, Affiliated to Osmania University
Hyderabad, Telangana, India

E mail id: abegum719@gmail.com

Abstract: The purpose of this review on floating drug delivery systems is to compile current research with a specific focus on polymers used in floating drug delivery systems, which are mostly of natural origin. Because the floating drug delivery system is less dense than stomach fluids, it can float in the upper gastrointestinal tract for an extended period of time, releasing the medicine at the appropriate rate. This is possible by using a variety of polymeric materials, including natural polymers. Despite the introduction of synthetic biodegradable polymers, a variety of polymeric materials are available to serve as release retarding floating matrices; however, the use of natural polymers to delay drug delivery is an ongoing research topic. Natural polymers are appealing because they are abundant in nature, are inexpensive, are made by living creatures, degrade easily in vivo, and are non-toxic

Keywords : Floating drug delivery system, natural polymers.

INTRODUCTION:

Gastric emptying of dosage forms is a highly variable process, and the ability to extend and control the emptying time is a crucial asset for dosage forms that stay in the stomach for longer than conventional dosage form. Designing controlled release systems for improved absorption and bioavailability presents a number of challenges. ^[1,2,3] Drug absorption from the gastrointestinal system is a complicated process that is influenced by a number of factors. It is well accepted that the amount of medication absorption in the gastrointestinal tract is proportional to the amount of time the drug spends in touch with the small intestine mucosa. As a result, for medications that are only partially absorbed, small intestinal transit time is an essential metric. ^[4] Gastro retentive systems can stay in the gastric region for several hours, significantly extending the time drugs spend in

Uma Rani *et al*/International Journal of PharmTech Research, 2022,15(2):58-65.

DOI: <http://dx.doi.org/10.20902/IJPTR.2022.150205>

the stomach. Prolonged stomach retention improves bioavailability, minimises drug waste, and improves solubility for medicines that are less soluble at high pH. It can also be used to deliver drugs to the stomach and proximal small intestines. Gastro retention aids in the provision of innovative drugs with novel treatment possibilities and significant patient advantages.^[5]

FDDS [FLOATING DRUG DELIVERY SYSTEM]:

These are low-density systems with a lower density than gastric fluid, allowing them to float in the stomach for longer periods of time without affecting the gastric emptying rate.

The FDDS are classified into two groups:^{3-9.}

A. Effervescent system.

B. Non effervescent system.

A. Effervescent system:

Effervescent systems release carbon dioxide when they come into touch with stomach juices. Inside the inflated hydrocolloids, the carbon dioxide is trapped. This gives the dose form buoyancy, which allows it to float. Volatile liquids that gasify at body temperature may also be present in these systems.

B. Non effervescent system:

This type of system swells after ingesting gastric fluid to the point where it prevents them from exiting the stomach. Because they tend to stay close to the pyloric sphincter, these systems are also known as "plug type systems." Combining the drug with a gel-forming polymer, which swells in contact after oral administration while maintaining relative shape integrity and a bulk density of less than one, is one method for creating such dosage forms. Excipients that form gels, such as polycarbonate, polyacrylate, and polystyrene, are the most commonly used. This hydrocolloid begins to hydrate by first forming a gel on the dosage form's surface.

NATURAL POLYMERS USED IN THE PREPARATION OF FLOATING DRUG DELIVERY SYSTEMS:

Hydrocolloids: Hydrocolloids are gel-forming agents that swell when in contact with gastric fluid while maintaining relative shape integrity and bulk density less than the gastric content. For Eg: Acacia, pectin, agar, alginates, gellan gum, guar gum, okra gum, cashew gum, xanthan gum, gelatin, and casein are a few examples.¹²

Chitosan: Chitosan is a straight chain homopolymer composed of (1, 4 -2-acetamido-2deoxy D-glucose) units that is commercially obtained by hydrolysis of the amino acyl groups of chitins. Chitosan contains one primary amino acid and two free hydroxyl groups or glucose units. Hydrogels are formed when cationic amino groups react with a variety of multivalent anions. Increased deacetylation improves chitosan biocompatibility. The modification of chitosan was central to the preparation of hydrogels.²⁶⁻²⁸

Hascicek C et al. used direct compression to prepare gastric floating bi-layer tablets containing acetyl salicylic acid. Tablets, such as the HPMC K100M, had the slowest release pattern. The release rate was effectively modified for up to 8 hours by combining HPMC K100M and chitosan. The drug release was discovered to be governed by the Higuchi diffusion mechanism.²⁶

H. M. El-Nahas et al prepared Chitosan microspheres containing TMZ by a capillary extrusion procedure.

Xanthan gum (XG): Is a polysaccharide with a high molecular weight that is derived from specific species of bacteria. It is made by fermenting glucose with the gram-negative bacteria *Xanthomonas campestris*. It is naturally nontoxic and nonpathogenic. Xanthan gum is soluble in both cold and hot water, resulting in a highly viscous solution that is resistant to heat and pH changes. Xanthan gum is also used as an excipient for drug sustained release and has time independent release kinetics. Each xanthan gum repeat unit has five sugar residues, including two molecules of glucose, two molecules of mannose, and one molecule of glucuronic acid. At C-6, the mannose closest to the main chain carries a single group. Xanthan gum has also been combined with

guar gum to create floating drug delivery systems. It has also been derivatised to sodium carboxymethyl xanthan gum and cross-linked with aluminium ions to prepare microparticles as a protein delivery carrier.¹³⁻²⁴

S Venkata et al. prepared non-effervescent floating drug delivery systems of the poorly soluble drug carvedilol phosphate using solvent evaporation and melt granulation techniques with release retarding polymers/swellable polymers such as xanthan gum and poly ethylene oxide.²⁵

A. Kulkarni et al. used a direct compression technique to prepare a region selective bilayer tablet of atenolol and lovastatin using sodium starch glycolate as a super disintegrant, HPMC K100M and xanthan gum as release controlling polymers, and sodium bicarbonate as a gas generating agent.¹³

Okra gum: Okra gum is a natural polymer derived from the pods of the okra plant (*Abelmoschus esculentus*). It's been used as a binder, a hydrophilic polymer matrix, a suspending agent, and a bioadhesive agent. It has been reported that okra gum, obtained through traditional extraction, has the potential to be used as a film coating agent. At gastric pH, it remains insoluble. It swells dramatically and aids in the delay of drug release.³⁸

Rajamma AJ et al. prepared gastro-retentive ziprasidone HCl tablets using natural gums as sustained release carriers. The floating lag time was found to be longer at higher levels of okra gum and shorter at higher levels of HPMC K4M.³⁸

Gellan gum: Gellan gum is a polysaccharide with a high molecular weight derived from *Pseudomonas* species. It is a byproduct of the fermentation of the microbe *Sphingomonas elodea* and nontoxic gram-negative bacteria. Gellan gum is a deacetylated anionic extracellular linear polysaccharide composed of glucuronic acid, rhamnose, and glucose. Its structure is made up of four linked monosaccharides, including one glucuronic acid molecule and two glucose molecules. This gum has excellent gel strength, exceptional stability, flexibility, high clarity, good film forming ability, and thermally reversible gel characteristics. Gellan gum easily dissolves and hydrates in hot or cold water, forming a viscous solution. Various researchers have considered this gum as a potential carrier for various floating dosage forms.⁴⁸

Navjot Kanwar et. al prepared Pregabalin floating tablets by varying the concentrations of the gums (xanthan gum and guar gum), Carbopol 974P NF, and HPMC K100.

Starch: Starch is a natural polysaccharide composed of amylose that represents the linear fraction of this macromolecule. A modified starch containing a high percentage of amylose (70%) has been successfully used in the research and development of swellable hydrophilic matrices. Some of the properties of high amylose starch can be changed by esterifying, etherifying, and oxidising its hydroxyl groups, or by cross-linking with chemicals such as epichlorohydrin, sodium trimetaphosphate, and others. The lowest drug release rates demonstrated that cross linking reactions introduced interchain ester linkages into polymer structures.^{42,44-46}

Saritha M et al. prepared pioglitazone floating matrix tablets with Olibanum, starch acetate, and HPMC K15M and compared them to one another. The floating lag time of the starch-containing formulation was 4-7 minutes, and the floating duration was 44-48 hours. Olibanum>starch acetate>HPMC K15M.⁴⁷ were the release retardant characters.

Sodium alginate: Sodium alginate is a nontoxic, biodegradable copolymer composed of L-glucuronic acid and D-mannuronic sea weed species extracted via ion exchange. In aqueous media, it hydrates and swells. In an acidic medium, however, it swells and remains insoluble, contributing to the buoyancy and controlled release properties.³⁰⁻³²

Patel N et al. prepared a gastro retentive drug delivery system for glipizide tablets. In vitro drug release studies revealed that increasing the concentration of polymer (sodium alginate) in the formulation resulted in a lower rate of drug release and a longer total floating time.³³

LG (Locust Bean Gum): It is a natural polysaccharide that is translucent white at the edges and contains approximately 88% D-galacto-D-mannoglycan, 4% pentan, 6% protein, 1% cellulose, and 1% ash. The D-galactose to D-mannose ratio is roughly 20:80.^{37,38}

Salve PS et al. prepared gas-generating floating metformin hydrochloride tablets. The tablet formulation containing metformin hydrochloride, locust bean gum in a 1:1 ratio, and 10% sodium bicarbonate demonstrated 90% drug release in 8 hours. Due to the weak matrix forming tendency of locust bean gum, a faster drug release was observed in the formulation batch containing locust bean gum alone compared to xanthan gum alone.

Guar gum: Guar gum is a polysaccharide found in the seeds of the *Cymopsis tetragonolobus* plant (family Leguminosae). Guar gum has been used by researchers to create sustained release dosage forms, either alone or in combination. In the presence of water, it swells rapidly and forms a translucent suspension. Guar gum's contents are separated into water soluble and insoluble components. The water-soluble fraction contains approximately 85 percent Guaran gum, a high molecular weight hydrocolloid polysaccharide. Guaran hydrolysis yields 65 percent galactose and 35 percent mannose, both of which are linked together via glycosidic linkages. Guar gum mucilage has a viscosity similar to that of acacia mucilage and a viscosity similar to that of tragacanth mucilage. It has a thickness that is 5-8 times that of starch. It functions as a protective colloid, binding agent, disintegrant, emulsifier, and so on. Guar gum is compatible with the majority of other plant hydrocolloids, including tragacanth. It is incompatible with acetone, ethanol (95 percent), tannins, strong acids, and alkalis.^{14, 17, 22}

Navneeth K et al. prepared Atorvastatin calcium floating tablets with guar gum as a release retardant. The formulated batches were able to stay in the stomach for approximately 12 hours, resulting in improved drug solubility and bioavailability.¹⁷

Pectin: Pectin is a carbohydrate-like plant constituent with a high molecular weight that is made up primarily of chains of galacturonic acid units linked as 1,4- α -glucosides. Pectin is defined in the USP 32 as a purified carbohydrate product derived from a dilute acid extract of the inner portion of the rind of citrus fruits or apple pomace. It is primarily composed of partially methoxylated polygalacturonic acids. There are two types of pectin gelation characteristics. There are two types of gelation: high-methoxy and low-methoxy. Pectin is a complex polysaccharide that primarily consists of esterified D-galacturonic acid residues in a 1, 4glucoside chain. Pectin gel beads have been demonstrated to be an effective medium for controlling drug release in the gastrointestinal tract. Pectin has been used as a component in the preparation of mixed polymer microsphere systems in order to achieve controlled drug release.³⁵

Navneeth K et al. created Atorvastatin calcium floating tablets with guar gum as a release retardant. The formulated batches were able to stay in the stomach for approximately 12 hours, resulting in improved drug solubility and bioavailability. When compared to synthetic polymers, formulations containing natural polymers demonstrated a greater release retardant effect and more predictable drug release profiles.¹⁷

Casein: Casein can enclose bioactive molecules, modifying their release and/or improving their bioavailability. It has the ability to alter the dissolution of drugs from compacts. Because casein films have a high tensile strength, they are an acceptable film-coating for tablets. As cross linkers, natural genipin and a natural tissue enzyme, transglutaminase, were used to create novel casein-based hydrogels for the controlled release of bioactives.⁵⁵⁻⁵⁶

Based on its emulsifying and bubble-forming properties, Elzoghby AO et al. created casein floating beads to increase the residence time of drugs in the stomach. Casein-based micro particles entrapping bioactive molecules were created using emulsification-chemical cross linking with glutaraldehyde, enzymatic cross linking with transglutaminase, simple co-acervation, and electrostatic complexation.

Olibanum: Olibanum is an oleo gum resin extracted from the incised trunk of the tree *Boswelliaserrata* of the Burseraceae family, also known as Sallakiguggul, Salai gum, and Indian Olibanum. *Boswellia* species are found in tropical parts of Asia and Africa. Olibanum is primarily composed of an acid resin (56-60%), gum (30-36%), and volatile oil (3- 8 percent). Gum is primarily composed of arabinose, with a trace of xylose and galactose. It works well as a matrix former and micro encapsulating agent for controlled release.^{38,40,41}

Devi C et al. created pioglitazone sustained release floating matrix tablets using Olibanum gum and HPMC. Olibanum was used as a matrix former, and sodium bicarbonate was used as a gas generating agent. As floating enhancers, bee's wax and ethyl alcohol were also used.

Cashew gum (CG): Cashew gum is an exudate derived from *Anacardium occidentale* Linn stem bark (family, Anacardiaceae). Cashew gum is composed of 61 percent galactose, 14 percent arabinose, 7% rhamnose, 8% glucose, 5% glucuronic acid, and less than 2% other sugar residues. L-arabinose, L-rhamnose, D-galactose, and glucuronic acid are produced when the gum is hydrolyzed. The gum is made up of a highly branched galactan framework made up of chains of (13) linked β -D-galactopyranosyl units interspersed with (1-6) linkages. Because of its low cost, nontoxicity, biodegradability, and appropriate physicochemical properties, cashew gum has been extensively researched for a variety of pharmaceutical applications.⁴²

Sterculia gum: Gum sterculia is a dried exudation obtained from the stems and branches of "Sterculia Urens," an Indian tree in the Sterculiaceae family. Gum sterculia belongs to the class of gums that have galactouronan or galacturonorhamnan basal chains with D-galacturonic acid (or its 4-methyl ether residues in the interior chain (as terminal units in side chain attached to a variety of different sugar residue). Gum sterculia contains approximately 43% D-galacturonic acid, 13% D-galactose, and 15% L-rhamnose. Gum Karaya is a negatively charged colloid and a complex acidic polysaccharide with a high molecular weight. It was found to be suitable for the preparation of hydrophilic matrices, minimatrices, and microcapsules, among other things.^{49,50}

Singh B et al., prepared a gastro-retentive floating drug delivery system of pantoprazole by simultaneous ionotropic gelation of alginate and sterculia gum using BaCl₂ as a cross linker.

CONCLUSION:

Because of their biodegradability, biocompatibility, Eco friendliness, and widespread availability, natural polymers have been widely used in the design and synthesis of novel drug delivery systems. As a result, these natural polymers will broaden the scope of future drug delivery systems. According to our discussions, sodium alginate and xanthan gum have recently become popular for the development of floating drug delivery systems. There are several expensive synthetic polymers available, but sodium alginate and xanthan gum may be the best alternatives. Better floating dosage forms with improved floating lag time, floating duration, and drug release can be achieved with proper selection of natural polymers and their blending with other polymers. Plant-based materials can be modified to meet the requirements of drug delivery systems, making them a viable alternative to synthetic polymers in the development of controlled release floating dosage forms. Formulations made from such renewable and environmentally friendly plant resources can be regarded as promising floating matrix forming agents for achieving sustained release action with site specific delivery for improved bioavailability, as supported by further research in this area. Despite its numerous advantages, this drug delivery system has seen very few industrial applications to date. With a decrease in dosing frequency, this delivery system may aid in the absorption of acidic active pharmaceutical ingredients.

REFERENCES:

- [1]. Singh N, Kim K.H, Floating drug delivery systems: an approach to oral controlled drug delivery via gastric retention, *J Control Release*, 2000,63, 235-59.
- [2]. Hirtz J, The GIT absorption of drugs in man: a review of current concepts and methods of investigation, *J. Clin. Pharmacol.*,1985, 19,77S-83S.
- [3]. Kumar AJ, Senthilanthan B, and Ravichandiran V, A review article on various types of floating drug delivery systems, *Int J Pharm PharmSci*, 4(1), 2012, 45-50.
- [4]. Arunachalam A, Karthikeyan K, Kishore K, Prasad PH, Sethuraman S, Ashuthoshkumar S, Manidipa S, Floating drug delivery systems: *Int J Res Pharm Sci*, 2(1), pp. 76-83, 2011.
- [5]. Yeole PG, Khan S, Patel VF, Floating drug delivery systems: Need and development, *Indian Journal of Pharmaceutical Sciences*, 67(3), 2005, 265-272.
- [6]. Pattan SR, Wani NP, Shelar MU, Nirmal SA, Chaudhari PD, Gude RS, The Scope and Importance of Floating Drug Delivery Systems, *Indian Drugs*, 49(10), 2012, 5-12.

- [7]. Shweta A, Ali J, Ahuja A, Khar RK, Baboota S, Floating drug delivery systems: Review, AAPS PharmSciTech, 6(3), 2005, E372- E390.
- [8]. Shah SH, Patel JK, Patel NV, Stomach specific floating drug delivery system: A review, Int J PharmTech Res, 1, 2009, 623–33.
- [9]. Prasad G, Rao GC, Studies on development and characterization of gastro retentive drug delivery system for antibiotics: Cefdinir, J Pharm Res, 6, 2013, 836-844.
- [10]. Chien YW, Novel drug delivery systems, 2nd edition, Informa health care, Newyork, 2000, 164-168.
- [11]. Robinson JR, Lee VHL, Controlled drug delivery fundamentals and applications, 2nd edition, Informa health care, Newyork, 2000, 500504.
- [12]. Kaushik YA, Tiwari KA, Gaur A, The Role of Excipients and Polymeric Advances in the Preparation of Floating Drug Delivery Systems, Int J Pharm Investg, 5(1), 2015, 1–12.
- [13]. Ajit K and Manish B, Development and evaluation of region selective bilayer floating tablets of atenolol and lovastatin for biphasic release profile, Iran J Pharm Res, 8(1), 2007, 15-25.
- [14]. Sanjay D, Sankha C, and Bhaskar M, Formulation and evaluation of a fixed dose combination of bilayer gastro retentive matrix tablet containing atorvastatin as a fast release and atenolol as a sustained release, Biomed Res Int, 2(1), 2014, 1-12.
- [15]. Harikrishna M, Rajesh A, Ramya MG, Neelima PVA, Naik VV, Formulation and evaluation of carvedilol and atenolol bilayered floating tablet, Der PharmaLett, 6(6), 2014, 403-414.
- [16]. Brijesh SD, Avani FA, Madhabhai MP, AAPS PharmSciTech, 5(2), 1-6, 2004. Ranitidine hydrochloride gastrointestinal drug delivery system: formulation and in vitro evaluation
- [17]. Navaneetha K, Reddy BV, Functionality comparison of natural and synthetic polymers in the development and in vitro characterization of an atorvastatin calcium-retentive floating drug delivery system, Indo Am J Pharm Res, 3(10), 2013, 1-10.
- [18]. Mundade S, Hosmani A, Thorat Y, Optimization of controlled release gastro retentive buoyant tablet with xanthan gum and polyox WSR 1105, Dig J Nano Med BiolStr, 9(3), 2014, 1077-1084.
- [19]. Swathi JC, Chandrakala RP, Polyox and xanthan gum coated floating pulsatile delivery of sumatriptan succinate in migraine treatment, Biomed Res Int, 2014, 11-10.
- [20]. Swathi JC, Suryawanshi VM, Pandya SV, Kuchekar BS, Chabukswar AR, Development of Press-Coated, Floating-Pulsatile Lisinopril Drug Delivery, Sci Pharm, 82, 423–440, 2014.
- [21]. Dey S, Mazumder B, Chattopadhyay S, Das MK, Sinha S, Shantanu G, Kakali D, and Mishra M, Polymers derived from xanthomonas campestris and Cymopsis tetragonolobus used as retardant materials in the formulation of a sustained release floating matrix tablet of atenolol, Int J Biol Macromol, 65, 346-35.
- [22]. Bueno VB, Bentini R, Catalani LH, and DFS Petri, Synthesis and swelling behaviour of xanthan-based hydrogels. CarbohydrPolym, 92(2), 1091-1099, 2013.
- [23]. Prakash U, Singh L, Sharma V, Role of xanthan gum (*Xanthomonas campestris*) in Gastro retentive drug delivery system: an overview, Int Res J Pharm, 4(4), 2013, 35-38.
- [24]. Rowe RC, Shesky PJ, Quinn ME, RPS Publishers, London, 2009, Handbook of Pharmaceutical Excipients, 6th Ed.
- [25]. Preparation and in vitro characterization of a noneffervescent floating drug delivery system of the poorly soluble drug carvedilol phosphate, Acta Pharm, 64, 2014, 485-494, Srikanth MV, Vanitha A, Weeliang PH, Dharmalingam SR, Ravi S.
- [26]. Hascicek C, Tilkan GY, Turkmen B, Ozdemir N, Effect of formulation parameters on drug release and floating properties of gastric floating two-layer tablets containing acetyl salicylic acid, Acta Pharm, 61, 303-312.
- [27]. Giri TK, Amrita T, Alexander A, Ajazuddin, Hemant B, Tripathi DK, Modified chitosan hydrogels as drug delivery and tissue engineering systems: present status and applications, ActaPharmSin B, 2(5), 439-449, 2012.
- [28]. Chavda H, Patel C, Chitosan super porous hydrogel composite-based floating drug delivery system: A novel formulation approach, J Pharm Bioallied Sci, 2(2), 124–131, 2010.
- [29]. Razavi M, Nyamathulla S, Karimian H, Ibrahim M, Noordin, Novel swellable orchidaceae polymer for famotidine gastro-retentive drug delivery, Drug Design DevTher, 8, 2014, 1315-1329.
- [30]. Spandana ADS, Neelofar SS, Sabiya SS, Ramana BV, Nagarajan G, Formulation and evaluation of simvastatin and lovastatin bilayer floating tablets, J Chem Pharm Res, 6(12), 2014, 186197.

- [31] Shaheen S, Sushma T, Devender S, Ahmad R, Venu M, Aseem B, Ahmad FJ, an approach for lacidipine loaded gastro retentive formulation prepared by different methods for diabetic gastroparesis, Saudi Pharm J, 21, 2013, 293-304.
- [32]. Controlled-release effervescent floating matrix tablets of ciprofloxacin hydrochloride: development, optimization, and in vitro–in vivo evaluation in healthy human volunteers, Europ J Pharm Biopharm, 74, 2010, 332-339.
- [33]. Patel N, Patel J, Modasiya M, Formulation and in vitro evaluation of glipizide as floating drug delivery system, Asian JTechnol, 2(2), 67-73, 2012.
- [34] Peter D., Tivadar P., Sandor N., Szilard P., and Attila D., Influence of different types of low substituted hydroxyl propyl cellulose on tableting, disintegration, and floating behaviour of floating drug delivery systems, Saudi Pharm J, 2015, 1-9.
- [35] Fernanda M, Carbinetto, Ana DC, Raul CE, Beatriz SFC, Insights into the swelling process and drug release mechanisms from cross linked pectin/high amylose starch matrices, Asian J Pharm Sci, 9, 2014, 27-34.
- [36] Ela ASFA, Hassan MA, Maraghy DAE, Ketorolac tromethamine floating beads for oral administration: characterization and invitro/in vivo evaluation, Saudi Pharm J, 22, 2014, 349-359.
- [37] Swathi JC, Patil S, Kuchekar BS, Design of Experiment for Tapentadol Hydrochloride Floating Drug Delivery, Comput Math Methods Med, 2013; 2013: 625-729.
- [38] Rajamma AJ, Yoogesh HN, Sateesha SB, Natural gums as sustained release carriers: development of a gastro-retentive drug delivery system for ziprasidone HCl, DARU J Pharm Sci, 20(1), 2012, 58
- [39] Salve PS, Development and in vitro evaluation of metformin hydrochloride gas-generating floating tablets, Asian J Res Pharm Sci, 1(4), 2011, 105-112.
- [40] Saritha M, Chowdary KPR, Ratna JV, Formulation of pioglitazone floating tablets: a comparison of olibanum, starch acetate, and HPMC K15M, J Glob Trend Pharm Sci, 4(3), 2013, 1237-1243.
- [41]. Devi GC, Rao RB, Formulation and evaluation of sustained release floating tablets of pioglitazone employing olibanum gum and HPMC, Asian J Pharm Clin Res, 5(1), 2012, 157-160.
- [42]. Monterio SS, Kamath SS, Nayak S, Prabhu SC, Shabaraya AR, Development and in vitro evaluation of floating microspheres of clarithromycin using rate controlling polymer, Int J Pharm Res Bio Sci, 3(3), 2014, 282-297.
- [43]. Paula HC, de Olivera EF, Abreu FO, de Paula RC, Alginate/Cashew gum floating beads as a matrix for larvicide release, Mater SciEng C Mater BiolAppl, 32(6),2012, 1421-1427.
- [44]. Narendra C, Srinath MS, Ganesh B, Optimization of bilayer floating tablet containing metoprolol tartrate as a model drug for gastric retention, AAPS PharmSciTech, 7(2), 2006, E1-E7.
- [45]. Dhinakaran SK, Kumar S, Banji D, Harani A, Venkateswar R, Formulation and evaluation of bilayer floating tablets of ziprasidone HCl and trihexyphenidyl HCl, Braz. J PharmSci, 47(3), 2011, 545-553.
- [46]. Saijan A, Natasa SB, Stability of amlodipine besylate and atenolol in multi component tablets of mono layer and bi layer types, Acta Pharm, 58, 2008, 299-308.
- [47]. Saritha M, Chowdary KPR, Ratna JV, Formulation of pioglitazone floating tablets: a comparative evaluation of olibanum, starch acetate and HPMC K15M, J Glob Trend Pharm Sci, 4(3), 2013, 1237-1243.
- [48]. Bhavesh S, Surendra G, Sanjay S, Formulation and evaluation of bilayer tablet of metoclopramide hydrochloride and ibuprofen, AAPS PharmSciTech, 9(3), 2008, 818-827.
- [49]. Singh B, Chauhan D, Barium ions crosslinked alginate and sterculia gum-based gastro retentive floating drug delivery system for use in peptic ulcers, Int JPolymer Mater Polym Bio Meter, 60(9), 2011, 156-169.
- [50]. Ashok CA, Poddar SS, Abdul S, Gaurav SE, Evaluation of sterculiafoetida gum as controlled release excipient, AAPS PharmSciTech, 9(1), 2008, 197-204.
- [51]. Ging ZY, Jun XB, Gan X, Advance in the applications of konjacglucomannan and its derivatives, CarbohydrPolym, 60(1), 2005, 27-31.
- [52]. Wang Y, Liu J, Li O, Wang Y, Wang C, Two natural glucomannan polymers, from Konjac and Bletilla, as bioactive materials for pharmaceutical applications, BiotechnolLett, 37(1),2015, 1-8.
- [53]. Wang K, He Z, Alginate konjacglucomannan chitosan beads as controlled release matrix, Inter J Pharm, 244(1-2), 2002, 117-126.
- [54]. Liang H et al., Fabrication of gastric floating controlled release tablet based on konjacglucomannan, Food Res Int, 72, 2015, 47-53.

- [55]. Elzoghby AO, El-Fotoh WS, Elgindy NA, Casein based formulations as promising controlled release drug delivery systems, J Control Release,153(3), 2011, 206-216.
- [56]. Bulgarelli E, Forni F, Bernabei MT, Effect of matrix composition and process conditions on casein gelatin beads floating properties, Int J Phram, 198(2), 2000, 157-165.
